




CW614N

TECHNICAL SHEET



BRASS RODS

INTERNATIONAL REFERENCES

EGM PB3	EN CuZn39Pb3	DIC CEN CW614N	ASTM(CDA) C38500	AFNOR CuZn40Pb3	BS CZ121	JIS C3604
------------	-----------------	-------------------	---------------------	--------------------	-------------	--------------

MAIN CHARACTERISTICS

Standard alloy for turnings applications. Excellent workability due to its relatively high lead content and its balanced percentage of beta phase.

CHEMICAL COMPOSITION

Cu [%]	Pb [%]	Sn [%]
57,0 - 59,0	2,5 - 3,5	≤ 0,3

Rev. 05/23

PHYSICAL PROPERTIES

Density	8.46g/cm ³
Electrical Conductivity	13.8MS/m
Electrical Conductivity	24IACS %
Thermal Conductivity	123W/mK


MECHANICAL PROPERTIES

Temper	Diameter / Wrench size [mm]	Tensile Strength Rm [N/mm ²]	Yeld Strength Rp0.2 [N/mm ²]	Elongation A [%]	Hardness HB
M	7 - 75	(340 - 550)	(180 - 450)	(10 - 40)	(110 - 140)

Please note: The mechanical properties are indicative only.


TYPES AND FORMAT AVAILABILITY

	Nominal Diameter [mm]		Tolerances [mm]		
	>	≤	Type A (standard tolerances)	Type B	Type C
	> 7	10	+0 / -0,06	+0 / -0,036	+0 / -0,025
	10	18	+0 / -0,07	+0 / -0,043	
	18	30	+0 / -0,08	+0 / -0,052	
	30	50	+0 / -0,16	-	
	50	75	+0 / -0,16	-	


	Width across-flats (W mm)		Tolerances (mm)	
	>	≤	Type B	
	> 7	10	+0 / -0,09	
	10	18	+0 / -0,11	
	18	30	+0 / -0,13	
	30	45	+0 / -0,16	

Rev. 05/23

SHAPES OF THE ENDS



Shaped ends of rod chamfered (mm)					
$\emptyset$		P (point)		S (chamfer)	
>	≤	min.	max.	min.	max.
7	10	2	3,5	2	3,5
10	20	2	4,5	2	4,5
20	30	3,5	6,5	3,5	6,5
30	42	4	6,5	4	6,5
43	75	6	8	6	8



Shaped ends of rod pointed (mm)					
Ch.		P (point)		S (chamfer)	
>	≤	min.	max.	min.	max.
7	10	2	3,5	0,4	1,5
10	20	2	4,5	0,5	2
20	32	3,5	6,5	0,6	2,5
32	45	5	8	1	4

Please note: The minimum and maximum measurements for the ends are indicative only. Specific requirements regarding the length of the ends must be evaluated and agreed in the time of order.

Rev. 05/23

LENGHTS AND STRAIGHTENINGS

		Lenght	
>	≤	Lenght (mm)	Tolerances (mm)
> 7	42	3050	+ 50
42	75	3050	+ 100
Maximum deviation from straightness			
>	≤	Localized over any 400 mm	Over whole lenght L of rod in metres L ≥ 1 m
> 7	50	0,4 mm	1,0 X L

		Lenght	
>	≤	Lenght (mm)	Tolerances (mm)
> 7	30	3050	+ 50
30	45	3050	+ 100
Maximum deviation from straightness			
>	≤	Localized over any 400 mm	Over whole lenght L of rod in metres L ≥ 1 m
> 7	50	0,6 mm	1,5 X L

Please note: The straightening has to be measured according to paragraph 6.5.3 of Norms EN 12164:2016).

OTHER SERVICES

All the turning rods (from Ø7 to Ø75 and from Ch.7 to Ch.45) are supplied in nominal lengths of 3000 mm, with point (P) and chamfer (S). Upon request, the product can be supplied with ends other than those indicated and with nominal lengths up to 5000 mm. the product is supplied in bundles of about 1000 kg closed by 3 or 4 metal strapping and paper between rods and metal strappings. Packaging with other characteristics must be evaluated and agreed upon when ordering.

Rev. 05/23